

Characterization of the Crystalline Structure of Wheat Bran Burned by Nd: YAG Laser

Muna A. Pn Gawbah^{1,2}, Ali A. S. Marouf^{3*}, Yousef A. Alsabah^{1,4}, Mohammed U. Orsod⁵, Abdelrahman A. Elbadawi^{1,6}

¹Department of Physics, Faculty of Science and Technology, Al Neelain University, Khartoum, Sudan

²Physics department, Faculty of Education-Seyoun, Hadhramout University, Hadhramout, Yemen

³Institute of Laser, Sudan University of Science and Technology, Khartoum, Sudan

⁴Department of Physics, Faculty of Education and Applied Science, Hajjah University, Hajjah, Yemen

⁵College of Science, Sudan University of Science and Technology, Khartoum, Sudan

⁶Faculty of Basic Studies, Future University, Khartoum, Sudan

Original Research Article

*Corresponding author

Ali A. S. Marouf

Article History

Received: 02.02.2018

Accepted: 12.02.2018

Published: 28.02.2018

DOI:

10.21276/sjeat.2018.3.2.6



Abstract: This paper reports obtaining of useful and highly value materials from wheat bran. For this purpose, wheat bran sample was burned for 30 s using Nd: YAG laser with output power 60 W. The product of synthesis process and non-burned wheat bran were characterized by x-ray diffractometer (XRD), energy dispersive x-ray (EDX) and fourier transform infrared (FTIR) so as to investigate its crystal structure and chemical components. XRD results of the sample before burning process revealed amorphous silica, cubic phase of silicon carbide and rhombohedral phase of carbon. The obtained results showed that burning process using Nd: YAG laser can convert the cubic structure of silicon carbide into hexagonal and rhombohedral structure and convert rhombohedral structure of carbon into hexagonal structure; also it revealed a monoclinic structure of silica after burning. FTIR showed a number of absorbance peaks assigned to silica and silicon carbide.

Keywords: Crystal Structure, EDX, FTIR, Laser Matter Interaction, Moissanite, Wheat Husk, Wheat Straw, Silica, XRD.

INTRODUCTION

Critical economic and environmental fettle of the current days hearten researchers and companies to improve and develop technologies purposed to reduce industrial wastes. As a consequence, much effort has been expended in different areas, including the agricultural outputting [1]. As an example, rice husk is an agricultural byproduct whose main constituent is organic material and hydrated silicon [2].

The use of rice husk has the benefit of producing valuable silica and silicon carbide, also of reducing disposal and pollution problems. Many researches show that amorphous silica can be prepared from a rice husk [1,3,5,6] and rice straw [3,7]. Della *et al.* reported that a 95% silica powder could be produced after heat-treated at 700°C for 6 hours. Real *et al.* in 1996 found that by mineral acid leaching silica of >99% purity can be obtained when burning rice husks at 600°C under an inert atmosphere [8]. Furthermore, charring of rice husk produces nanosize silica carbon called (nanosil) intermixed composite which may find newer application because such product is not available synthetically, this may directly be converted to silicon carbide and silicon nitride at high temperature [1-3].

Also wood is a renewable naturally occurring resource; Sene *et al.* in 1994 and Ye *et al.* in 2017 found a facile approach is reported to transform wood into hierarchical porous graphene using CO₂ laser

scribing [9,10]. They show that laser-induced graphene (LIG) can be formed on the wood surface to provide high electrical conductivity for graphene. They depicted the surface of square of pine wood is converted to 3D porous graphene when irradiated by a 10.6µm CO₂ laser under Ar or H₂ at room pressure.

However wheat husk, which also containing silica, there are two forms of silica after burning process, amorphous silica and crystalline silica [11] and wheat, their ashes contain >90% silica by mass with minor amounts of metallic elements, making it another economical source of nanoscale silica in the future [2,9].

In this paper, we burned wheat bran by a 1.064µm Nd: YAG laser with 60 W output power. The advantage of Nd: YAG laser comes from its high gain and good thermal properties; it is the most important solid-state laser for scientific, medical, industrial, and

military applications [12-14]. The laser heat was used instead of the heat of the furnace in burning wheat bran and this method saved time, power and effort. We study wheat bran before and after burning. The physical and chemical characterizations selected in this study included XRD, EDX, FTIR and Digital Microscope. The objective of the recent work is to obtain useful and valuable materials like silica and silicon carbide from wheat bran burning using Nd: YAG laser.

Experimental

Wheat bran sample was collected from (Tuti Island, in Khartoum, Sudan). It was washed with distilled water many times to remove adhering soil and other contaminants then dried at room temperature after that it was milled. One gram of the sample was placed into a high temperature glass beaker (schott duran - Germany) and it was burned on the air by the heat of Nd: YAG laser (Dornier Medilas fibertom 5100) beam with output power 60W for 30 s. The laser beam was delivered by single mode fiber optic with diameter 125 μm . The distance between the sample and the end of the fiber optic was 1 cm. Because of the small spot size of the laser beam the process of burning was done point by point laser was fixed on holder and the high temperature glass beaker was rotated every 30 s carefully for 5 mm displayed in Figure 1, this experiment repeated many times before investigations for accuracy. Microscopic photograph for the burned wheat bran was done by (Digital Microscope 400X Digital Zoom. Samples were examined before and after burning by XRD (Shimadzu, MAX_X, XRD-7000) using $\text{Cu K}\alpha$ with scanning speed of 1000 $^\circ$ /mi. The samples were prepared by grinding before XRD measurements carefully by agate mortar for homogeneity. EDX spectrometer was employed to characterize burned and non-burned wheat bran samples for this (Shimadzu - EDX- 8000) was operated at 4KV to 50KV. The chemical groups presented in burned and non-burned wheat bran samples were identified by the FTIR spectrometer (Satellite FTIR 5000) in the wavenumber rang of (400-4000) cm^{-1} .

RESULTS AND DISCUSSIONS

XRD Results

The X-ray diffraction patterns were shown in Figure 2; it showed amorphous structure (including multi phases), Figures 3 and 4 showed the analyzed spectra for the wheat bran samples before and after burning analyzed by MDI jade 0.5 match program [15], graphs obtain the presence of the amorphous silica in the two samples, at the normal broad peak at $2\theta=21.7-21.8$ for the samples before and after burning respectively. It also indicates that burning process using laser is very effective to change the wheat bran from amorphous phase into crystalline structure phase. Therefore, several phases were appeared in the samples. In non-burned wheat bran graph the phases peaks were appeared at $2\theta=26.57$ which refer to Carbon (C) phase,

at $2\theta=37.8, 43.99, 64.397$ and 77.509 these peaks refer to silicon carbide (SiC) structure [16].

Also there are several phases appeared after burning process that shown at $2\theta=37.74$ Moissanite - 33R (SiC) [17], $2\theta=43.74, 64.38$ and 77.48 silicon carbide (SiC), $2\theta=45.75$ and 50.19 Carbon (C), $2\theta=59.74$ Coesite, syn SiO_2 and at $2\theta=86.03$ and 75.74 that refer to the Moissanite -5H SiC (Dark - blue)[18]. That also shown the peaks intensity and appearance was obtained with burn process. Tables 1 and 2 showed the details of the XRD result. Digital microscope image in Figure 5 confirms the presence of moissanite.

FTIR Analysis

FTIR spectra were investigated for the burned and non-burned wheat bran samples that showed graphene and silicon bonds (see Figure 6). The absorbance peak around the 3434 cm^{-1} was due to the adsorbed water in the wheat bran samples after and before burning process [2], Also it may be refer to the OH stretching and vibration. The peak around 2940 cm^{-1} can be assigned to the C-H stretching modes and the CH_2 group was presented at around 2940 cm^{-1} as asymmetric stretching. The absorbance peak around 2344.31 cm^{-1} obtained to $-\text{C}\equiv\text{N}$ - (Nitrites) and $-\text{C}\equiv\text{C}-$ (Alkynes) compounds [19]. A strong peak at 1630 cm^{-1} assigned to the Aromatic stretching in wheat bran structure and it became higher after burning process [2, 9, 19]. The absorbance bond at 1422 cm^{-1} peak refers to C-O vibrations or to C-H deformation in the samples [20, 21]. In generally, the 1422 cm^{-1} peak appear due to C-O stretching of carbonate [22]. The absorbance peak around 1110 cm^{-1} assigned to the Si-O-Si anti-symmetric stretching mode and the peaks around 660 cm^{-1} and 420 cm^{-1} correspond to siloxane bonds (Si-O-Si) stretching and bending vibrations [2, 20]. The FTIR results came to confirm the XRD results when the (SiC) synthetic moissanite is characterized by the peaks at range between $2400 - 1200 \text{ cm}^{-1}$ [23].

EDX Results

The EDX result was investigated using (Shimadzu, EDX- 8000), table 3 showed the weight of the elements in the samples of wheat bran before and after burning respectively. The X-ray passed through particles of the wheat bran samples to detect the presence of element specially the concentration of the carbonate [24]. It was observed that the concentration of some elements in the sample increased after burning of wheat bran, this is because a quantity of carbon evaporated in the form of carbon dioxide during combustion (see Figure 7).

CONCLUSIONS

Wheat bran has silica contents which can be utilized to produce various useful materials. The possibility of producing silica and silicon carbide from wheat bran was achieved in this study by burning it by Nd: YAG laser. XRD results showed amorphous silica, cubic phase of silicon carbide and rhombohedral phase of carbon before burning. It was found that this burning

process caused in converting the cubic structure of silicon carbide into hexagonal and rhombohedral structure, and it converted rhombohedral structure of carbon into hexagonal structure, a monoclinic structure of silica also was found after burning. FTIR showed a number of absorbance peaks assigned to silica and silicon carbide.

ACKNOWLEDGEMENTS

Authors would like to thank Ms. Areej Ahmed, research assistant at Institute of Laser, Sudan University of Science and Technology, for her support in setup and implementation of the experiments. Also, many thanks for Department of Laser at Al Neelain University for their effort in conducting FTIR test for our samples including calibration and operation of FTIR instrument.

REFERENCES

1. de Sousa, A. M., Visconte, L., Mansur, C., & Furtado, C. (2009). Silica sol obtained from rice husk ash.
2. Chen, H., Wang, F., Zhang, C., Shi, Y., Jin, G., & Yuan, S. (2010). Preparation of nano-silica materials: The concept from wheat straw. *Journal of Non-Crystalline Solids*, 356(50-51), 2781-2785.
3. Della, V. P., Kühn, I., & Hotza, D. (2002). Rice husk ash as an alternate source for active silica production. *Materials Letters*, 57(4), 818-821.
4. Liou, T. H. (2004). Preparation and characterization of nano-structured silica from rice husk. *Materials Science and Engineering: A*, 364(1-2), 313-323.
5. Singh, D., Kumar, R., Kumar, A., & Rai, K. N. (2008). Synthesis and characterization of rice husk silica, silica-carbon composite and H₃PO₄ activated silica. *Cerâmica*, 54(330), 203-212.
6. Mehta, A., & Ugwekar, R. P. (2015). Extraction of Silica and other related products from Rice Husk. *International Journal of Engineering Research and Applications*, 5(8), 95-98.
7. Nandiyanto, A. B. D., Rahman, T., Fadhlulloh, M. A., Abdullah, A. G., Hamidah, I., & Mulyanti, B. (2016, April). Synthesis of silica particles from rice straw waste using a simple extraction method. In *IOP Conference Series: Materials Science and Engineering* (Vol. 128, No. 1, p. 012040). IOP Publishing.
8. Real, C., Alcalá, M. D., & Criado, J. M. (1996). Preparation of silica from rice husks. *Journal of the American ceramic society*, 79(8), 2012-2016.
9. Sene, C. F., McCann, M. C., Wilson, R. H., & Grinter, R. (1994). Fourier-transform Raman and Fourier-transform infrared spectroscopy (an investigation of five higher plant cell walls and their components). *Plant Physiology*, 106(4), 1623-1631.
10. Ye, R., Chyan, Y., Zhang, J., Li, Y., Han, X., Kittrell, C., & Tour, J. M. (2017). Laser-Induced Graphene Formation on Wood. *Advanced Materials*, 29(37).
11. Naqvi, H. J., Saeed, A., Umair, A., & Tajwar, S. (2011). Precipitated silica from wheat husk. *JPICHE*, 39, 51-54.
12. Walter, J. L. (1982). *The Infrared Spectra of Complex Molecules*.
13. Sato, T., Fujimoto, Y., Ueda, T., Fujinoki, A., Okada, H., Yoshida, H., ... & Nakatsuka, M. *Solid-State Laser Engineering Solid-State Laser Engineering*, 1999.
14. Koechner, W. (2013). *Solid-state laser engineering* (Vol. 1). Springer.
15. Martínez-Casillas, D. C., Vázquez-Huerta, G., Pérez-Robles, J. F., & Solorza-Feria, O. (2011). Electrocatalytic reduction of dioxygen on PdCu for polymer electrolyte membrane fuel cells. *Journal of Power Sources*, 196(10), 4468-4474.
16. Jin, G. Q., & Guo, X. Y. (2003). Synthesis and characterization of mesoporous silicon carbide. *Microporous and mesoporous materials*, 60(1-3), 207-212.
17. Liu, P., Yao, P., & Liu, J. (2008). Effect of SiC nanoparticle additions on microstructure and microhardness of Sn-Ag-Cu solder alloy. *Journal of Electronic Materials*, 37(6), 874-879.
18. Capitani, G. C., Di Pierro, S., & Tempesta, G. (2007). The 6 H-SiC structure model: Further refinement from SCXRD data from a terrestrial moissanite. *American Mineralogist*, 92(2-3), 403-407.
19. Bellamy, L. J. (1975). Amides, proteins and polypeptides. In *The Infra-red Spectra of Complex Molecules* (pp. 231-262). Springer, Dordrecht.
20. Chang, Q., Hao, X., & Duan, L. (2008). Synthesis of crosslinked starch-graft-polyacrylamide-co-sodium xanthate and its performances in wastewater treatment. *Journal of hazardous materials*, 159(2-3), 548-553.
21. Tse, K. C. C., Nikezic, D., & Yu, K. N. (2007). Comparative studies of etching mechanisms of CR-39 in NaOH/H₂O and NaOH/ethanol. *Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms*, 263(1), 300-305.
22. Sahoo, S., Seydibeyoğlu, M. Ö., Mohanty, A. K., & Misra, M. (2011). Characterization of industrial lignins for their utilization in future value added applications. *Biomass and bioenergy*, 35(10), 4230-4237.
23. Țucureanu, V., Matei, A., & Avram, A. M. (2016). FTIR spectroscopy for carbon family study. *Critical reviews in analytical chemistry*, 46(6), 502-520.
24. Wang, L., Skreiberg, Ø., Becidan, M., & Li, H. (2016). Investigation of rye straw ash sintering characteristics and the effect of additives. *Applied energy*, 162, 1195-1204.